

# **Technical Information**

Product name : MoTip Lacquer, white

Gloss 500 ml : Matt High gloss Article number : 04002 04004

Gloss 150 ml : High gloss Article number : 00107

Supplier / Producer : MOTIP DUPLI B.V.

Wolfraamweg 2

**NL-8471 XC WOLVEGA** 

Telephone number +31 561 - 69 44 00 Telefax number +31 561 - 69 44 31

## **Product description**

High quality, fast-drying lacquer to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

#### **Product characteristics**

Fast drying Good coverage

Lasting gloss

Non-fading and UV resistant

Good surface hardness

Resistant to petrol, chemicals and weather influences

Wear resistant and scratch free

**Excellent adhesion** 

# **Physical and Chemical Characteristics**

Contents : 500 ml 150 ml

Base : Acrylic resin

Colour : White

VOC-content : Approximately 88% w/w Solid Content : Approximately 12% w/w

Coverage : 1,5 to 2 m<sup>2</sup> Approximately 0,5 m<sup>2</sup>

Dust dry : After 5 to 10 minutes Tack free : After 10 to 20 minutes

Hardened/re-sprayable : After 2 hours Heat resistant : To 110°C

## Usage

Before use, carefully read the directions on the packaging and act accordingly.

#### **Pre Treatment**

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).

#### **Treat**

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.